

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B01J 37/00, C08G 65/10		A1	(11) International Publication Number: WO 98/52689 (43) International Publication Date: 26 November 1998 (26.11.98)
(21) International Application Number: PCT/EP98/02098 (22) International Filing Date: 9 April 1998 (09.04.98) (30) Priority Data: 08/857,998 16 May 1997 (16.05.97) US (71) Applicant (for all designated States except MN): ARCO CHEMICAL TECHNOLOGY, L.P. [US/US]; Two Greenville Crossing, Suite 238, 4001 Kennett Pike, Greenville, DE 19807 (US). (71) Applicant (for MN only): ARCO CHEMIE TECHNOLOGIE NEDERLAND B.V. [NL/NL]; (Theemsweg 14, 3197 KM Botlek Rotterdam), P.O. Box 7195, NL-3000 HD Rotterdam (NL). (72) Inventors: HAYES, John, E.; 17a, route de Boran, F-60270- Gouvieux (FR). LANGSDORF, Leah, J.; 516 N. Veron- ica Road, West Chester, PA 19380 (US). ISAACS, Bruce, H.; 48 Springhouse Lane, Media, PA 19063 (US). ARMELLINI, Fred, J.; 705 Moreland Road, Willow Grove, PA 19090 (US). (74) Agent: CROPP, John, Anthony, David; Mathys & Squire, 100 Grays Inn Road, London WC1X 8AL (GB).			(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: PROCESS FOR RAPID ACTIVATION OF DOUBLE METAL CYANIDE CATALYSTS			
(57) Abstract <p>A process for activating double metal cyanide catalysts is disclosed. A polyol starter or starter/catalyst mixture is heated under vacuum under conditions effective to achieve improved stripping compared with that which can be achieved through conventional vacuum stripping. Coupling vacuum stripping with inert gas sparging or stripping in the presence of an organic solvent gives a starter/catalyst mixture that activates rapidly in an epoxide polymerization process. Rapid activation makes process start-ups reliable and reduces cycle time. The process gives polyols with lower viscosity, lower polydispersity, and lower unsaturation for better polyurethanes.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LJ	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

PROCESS FOR RAPID ACTIVATION OF DOUBLE METAL CYANIDE CATALYSTS

5

FIELD OF THE INVENTION

The invention relates to double metal cyanide (DMC) catalysts. In particular, the invention relates to a process for stripping polyol starters or mixtures of a polyol starter and a DMC catalyst to prepare them for use in an epoxide polymerization reaction. Improved stripping results in rapid catalyst activation and/or improved polyols and polyurethanes.

10

BACKGROUND OF THE INVENTION

Double metal cyanide (DMC) complexes are well-known catalysts for epoxide polymerization and synthesis of polyether polyols. The catalysts were discovered in the 1960s (see, e.g., U.S. Pat. Nos. 3,278,459 and 3,829,505). Recent improvements have made DMC catalysts much more attractive for commercial manufacture of polyether polyols (see, e.g., U.S. Pat. Nos. 5,158,922, 5,426,081, 5,470,813, and 5,482,908). Compared with conventional KOH catalysts, DMC catalysts give fast epoxide polymerizations, so cycle times for polyol manufacture can be reduced. In addition, DMC catalysts give high-quality polyether polyol products that have low unsaturation, narrow molecular weight distribution, and low viscosity.

15

20

25

30

While DMC catalysts offer significant advantages, even the best DMC catalysts have some drawbacks. For example, unlike KOH, DMC catalysts must normally be activated before the epoxide can be added continuously to the reactor. Usually, a polyol starter and a DMC catalyst are combined and heated under vacuum prior to the addition of a small proportion of epoxide. Catalyst activation is inferred from a drop in epoxide partial pressure in the reactor. At typical epoxide/starter charges of 5-15 wt.%, initiation times (defined as the time required for a 50%

decrease in epoxide partial pressure) can range from several minutes to several hours. Long initiation times increase cycle time, which undercuts the economic advantage of faster polymerizations. In addition, heating the catalyst for a prolonged period at high temperature can reduce its activity or deactivate it completely.

Initiation time can be reduced by increasing epoxide concentration. However, higher initial epoxide concentrations can generate uncontrolled exotherms: a potential safety hazard. Temperature excursions can also negatively impact polyol quality (e.g., higher viscosity, broader molecular weight distribution). Increasing reaction temperature also reduces initiation time. However, reaction temperature can only be increased marginally without having adverse effects on polyol quality.

In sum, an improved way to activate DMC catalysts is needed. Preferably, the process would be simple to practice with inexpensive, readily available equipment and supplies. A preferred process would offer polyol makers that use DMC catalysts more control over initiation of epoxide polymerizations. A valuable process would activate catalysts within minutes (rather than hours) and would permit use of low starting concentrations of epoxides. A valuable process would give polyether polyols that have low viscosity, low polydispersity, and low unsaturation. Ideally, the resulting polyols would give improved polyurethane foams, sealants, elastomers, adhesives, and coatings.

SUMMARY OF THE INVENTION

The invention is a process for stripping polyol starters or mixtures of a polyol starter and a double metal cyanide (DMC) catalyst. In one process, a polyol starter is first combined and mixed with a DMC catalyst. The starter/catalyst mixture is then heated under vacuum under conditions effective to achieve improved stripping compared with that which can be achieved through conventional vacuum stripping. Preferred conditions

include vacuum stripping while sparging the mixture with an inert gas and vacuum stripping in the presence of an organic solvent. Alternatively, a polyol starter is vacuum stripped in the absence of a catalyst under conditions effective to achieve improved stripping, and the starter is
5 combined with a DMC catalyst later.

We surprisingly found that stripping starters and starter/catalyst mixtures as described above offers substantial advantages to polyol manufacturers. First, the starter/catalyst mixtures generally activate more rapidly (within minutes) in an epoxide polymerization process compared
10 with a starter/catalyst mixture that is simply vacuum stripped in the conventional way. Thus, the process makes start-ups reliable without prolonging cycle time. We also found that polyols made by the process have improved properties, including lower viscosity, lower polydispersity, and lower unsaturation compared with polyols made by a process that
15 uses conventional vacuum stripping alone. Finally, we found that improving starter/catalyst stripping can even improve properties of polyurethanes made from the polyols.

DETAILED DESCRIPTION OF THE INVENTION

The process of the invention comprises heating polyol starters or
20 starter/catalyst mixtures under vacuum under conditions effective to achieve improved stripping compared with that which can be achieved through conventional vacuum stripping.

Polyol starters contain one or more active hydrogen groups (-OH, -NH₂, etc.) and are capable of starting epoxide polymerizations. Polyol
25 starters have a lower molecular weight than the desired reaction product. Preferably, the starter has a number average molecular weight of at least about 200 and contains one or more hydroxyl end groups. Preferred polyol starters have average hydroxyl functionalities from about 1 to about 8. Compounds suitable as polyol starters are well known to those skilled

in the art. Examples include tripropylene glycol, polyoxyalkylene glycols, polytetramethylene ether glycols, propoxylated glycerol, alkoxyated allylic alcohols, and the like, and mixtures thereof. Other examples of suitable polyol starters are listed, for example, in U.S. Pat. No. 5,158,922, the teachings of which are incorporated herein by reference.

The process of the invention is valuable for activating catalyst/starter mixtures in which the starter is an alkoxyated allylic alcohol, particularly a propoxylated allyl alcohol having from one to five oxypropylene units. These starters are often difficult to activate otherwise. Alkoxyated allylic alcohols, including high molecular weight (> 2000) propoxylated allyl alcohols, are valuable intermediates for making silicone surfactants. Many of these surfactants have a hydrophobic silicone backbone and more hydrophilic polyether side chains attached by Si-C bonds. These "comb" polymers are made by grafting one or more alkoxyated allylic alcohols onto a silicone backbone using a transition metal catalyst. Examples appear in U.S. Pat. Nos. 5,525,640, 5,489,617, and 5,110,970, the teachings of which are incorporated herein by reference.

The process of the invention is used to activate double metal cyanide (DMC) catalysts. DMC catalysts are a well-known class of epoxide polymerization catalysts. Suitable DMC catalysts and methods of making them are described, for example, in U.S. Pat. Nos. 3,278,457, 3,829,505, 3,941,849, 4,472,560, 5,158,922, 5,470,813, 5,482,908, the teachings of which are incorporated herein by reference. Generally, aqueous solutions of a metal salt (e.g., zinc chloride) and a metal cyanide salt (e.g., potassium hexacyanocobaltate) are combined in the presence of an organic complexing agent (e.g., glyme, t-butyl alcohol) to produce a precipitate of the DMC complex. Zinc hexacyanocobaltates are particularly preferred.

Any DMC catalyst can be activated by the process of the invention, including, for example, the original DMC-glyme catalysts (see, e.g., U.S. Pat. Nos. 3,278,457, 3,829,505, 3,941,849, 4,472,560), newer DMC catalysts that are substantially non-crystalline (see, e.g., U.S. Pat. Nos. 5,470,813 and 5,482,908), DMC catalysts that incorporate about 2-80 wt.% of a polyether or other functionalized polymer such as polyacrylamides (see, e.g., U.S. Pat. No. 5,482,908 and Serial No. 08/731,495). ("Functionalized polymers" contain one or more functional groups containing oxygen, nitrogen, sulfur, phosphorus, or halogen, wherein the polymer, or a water-soluble salt derived from it, has relatively good water solubility, i.e., at least about 3 wt.% of the polymer or its salt dissolves at room temperature in water or mixtures of water with a water-miscible organic solvent.) The process of the invention is suitable for use with various forms of DMC catalysts, including powders, pastes (see, e.g., Serial No. 08/588,751), or suspensions (see U.S. Pat. No. 4,472,560). The process of the invention can be used to activate DMC catalysts used in batch, semi-batch, and continuous processes, and also to activate catalysts used in processes that involve continuous addition of some or all of the starter during polymerization.

The polyol starter or mixture of starter and DMC catalyst is heated and stripped under vacuum under conditions effective to achieve improved stripping compared with that which can be achieved through conventional vacuum stripping. Improved stripping compared with conventional vacuum stripping can be achieved in any desired way. Preferred approaches include inert gas sparging combined with vacuum stripping, wiped-film evaporation, vacuum stripping in the presence of an organic solvent, and the like. We surprisingly found that improved stripping of starters and starter/catalyst mixtures results in rapid catalyst activation and production of high-quality polyols.

The temperature at which the stripping is performed is not critical. Preferably, however, the stripping is performed at a temperature within the range of about 60°C to about 200°C; a more preferred range is from about 80°C to about 150°C. The stripping is performed at reduced pressure (less
5 than 760 mm Hg). Preferably, the stripping is performed at reactor pressures less than about 300 mm; more preferred are pressures less than about 200 mm.

The polyol starter can be stripped before adding the DMC catalyst. We found that reducing the water content of starters by improved stripping
10 offers faster catalyst activation and better polyols. Preferably, the water content of the starter is reduced to less than about 100 ppm; more preferably, the water content of the stripped starter is less than about 50 ppm. Water content of polyol starters can also be reduced by other methods known to those skilled in the art, including, for example, by
15 adding in-situ drying agents (e.g., magnesium sulfate, molecular sieves).

While the polyol starter can be stripped before adding the DMC catalyst, it is generally preferred to perform the stripping step with both starter polyol and DMC catalyst present. As Example 10 and Comparative
20 Example 11 below illustrate, catalyst activation is usually much faster if both starter and catalyst are present during vacuum stripping.

During vacuum stripping, the starter or starter/catalyst mixture can be sparged with an inert gas. Preferably, the sparging is performed in a manner effective to produce a starter/catalyst mixture that activates rapidly
25 in an epoxide polymerization. Suitable inert gases are those that can assist in removal of volatile impurities from starter/catalyst mixtures yet do not react with the starter or poison the DMC catalyst. Suitable inert gases include, for example, nitrogen, air (preferably dry air), carbon dioxide, argon, helium, and the like, and mixtures thereof. Sparging is normally performed by injecting the gas at one or more locations below the surface
30 of the starter/catalyst mixture. An aerating device can be used to further

distribute the gas. The flow rate of the inert gas is adjusted to produce maximum catalyst activation. Generally, a flow rate within the range of about 0.001 to about 0.1 pounds of gas per hour per pound of starter is preferred.

5 The degree of improvement conferred by improved stripping depends on many factors, including, for example, the initial water content of the starter polyol, the amount and type of catalyst, the nature of the starter, and the polyol product molecular weight. The particular stripping
10 conditions used are also important: the temperature, vacuum level, amount of inert gas used, and stripping time are adjusted to maximize efficiency in activating the starter/catalyst mixture and/or producing better polyols.

 Starter/catalyst mixtures prepared by the process of the invention activate more rapidly in an epoxide polymerization process compared with
15 starter/catalyst mixtures that are merely vacuum stripped in the conventional way. In fact, as the Examples in Tables 1-3 demonstrate, the catalysts have initial activities that are typically 5 to 20 times greater (compare the initial K_{app} values in Table 2) and initiation times that are usually 2 or 3 times shorter (see Tables 1 and 3).

20 Rapid activation has added advantages. Catalyst initiation is safer and more predictable when initial activity is high. In addition, because the starter/catalyst mixture can usually be activated during initial heating, cycle time is minimized. Fast activation also permits a faster epoxide feed ramp, less accumulation of unreacted epoxide in the reactor, and a greatly
25 reduced risk of unwanted temperature excursions. Such temperature excursions contribute to operational glitches and poor product quality.

 It is generally preferred to activate the starter/catalyst mixture by inert-gas sparging, but any other method can be used that provides a
30 greater degree of stripping than is possible using conventional vacuum stripping. A second preferred approach is to vacuum strip the mixture in

the presence of an organic solvent. Suitable solvents are those that assist in removing volatile impurities from the mixture without reacting with the starter or poisoning the catalyst. Suitable organic solvents include, for example, ethers (including tetrahydrofuran and propylene oxide), esters, ketones, alcohols, hydrocarbons, halogenated hydrocarbons, and the like, and mixtures thereof. The solvent can be added to the starter/catalyst mixture in one portion, multiple portions, or it can be introduced continuously during the vacuum stripping process. Preferably, the organic solvent is recovered, purified, and reused in the process. The amount of solvent used is that which is effective to produce a catalyst/starter mixture that will activate more rapidly in an epoxide polymerization process compared with starter/catalyst mixtures that are not vacuum stripped in the presence of an organic solvent.

One process of the invention comprises polymerizing one or more epoxides in the presence of the stripped starter/catalyst mixture to make a polyether polyol. Methods for making epoxide polymers using DMC catalysts are described completely in U.S. Pat. Nos. 3,829,505, 3,941,849, 5,158,922, 5,470,813, and 5,482,908, the teachings of which are incorporated herein by reference. Suitable epoxides include, for example, ethylene oxide, propylene oxide, butene oxides, styrene oxide, and the like, and mixtures thereof. The process can be used to make random or block copolymers.

Effective stripping improves polyol quality. Polyether polyols produced using the starter/catalyst mixtures have lower unsaturation, lower polydispersity (narrower molecular weight distribution), and lower viscosity compared with polyols made without activating the starter/catalyst mixture by the process of the invention. Low viscosity and low polydispersity make the polyol easier to process in downstream applications. Low unsaturation (low monol content) means a polyol with truer hydroxyl functionality and

polyurethanes with improved physical properties (e.g., tensile strength, tear strength, compression set).

5 Polyether polyols made by the process of the invention are valuable for making polyurethane foams, coatings, sealants, adhesives, and elastomers with improved properties. Molded flexible foams made from the polyols, for example, have cells that are more easily broken open by crushing compared with foams made using polyols not made by the process of the invention. As Example 28 shows, the foams have reduced force-to-crush ratios, which indicates high quality and good comfort.

10 The following examples merely illustrate the invention. Those skilled in the art will recognize many variations that are within the spirit of the invention and scope of the claims.

EXAMPLES 1-12

Effect of Improved Stripping on Catalyst Activation

15 These examples show that using an inert gas in combination with vacuum stripping is more effective than either conventional vacuum stripping or no stripping at all for activating double metal cyanide catalysts. The process of the invention is well-suited for activating the variety of DMC catalysts described in the art. For example, the process works with various
20 complexing agents in the catalyst (glyme, t-butyl alcohol) and with polyether-containing catalysts. The process also works with both powder and paste forms of the catalyst. Results appear in Table 1.

EXAMPLES 13-16

Effect of Improved Stripping on Initial Catalyst Activity

25 As the results in Table 2 show, stripping under vacuum with a nitrogen sparge has a dramatic impact on initial catalyst activity. The effect is nearly identical with either a 400 mol. wt. diol or 700 mol. wt. triol starter.

EXAMPLES 17-27

Effect of Improved Stripping on Polyol Properties

These examples show that using an inert gas in combination with vacuum stripping gives polyols with improved physical properties compared with polyols made in a process that uses either conventional vacuum stripping or no stripping at all. As the results in Table 3 show, vacuum stripping assisted by a nitrogen sparge results in faster catalyst initiation, lower polyol viscosity, narrower molecular weight distribution (M_w/M_n), and lower unsaturation.

10

EXAMPLE 28

Effect of Improved Stripping on Flexible Polyurethane Foam Properties

Flexible foams are prepared from TDI prepolymers as is described in Appl. Ser. No. 08/544,629, filed October 18, 1995. The TDI prepolymers are made by reacting one mole of TDI for each mole of polyol hydroxyl groups. The only difference is that Polyol A is made from a starter/DMC catalyst mixture that is vacuum stripped at 50 mm without any gas sparging prior to making the polyol, and Polyol B is made from a starter/DMC catalyst mixture that is vacuum stripped at 140 mm while being sparged with nitrogen at 0.01 pounds per hour of nitrogen per pound of starter. The foam made from Polyol A has foam force-to-crush values of 376/236/182 for cycles 1-3.

20

Table 1. Effect of Improved Stripping on Catalyst Activation					
Ex #	Catalyst ¹	Amt. ² (ppm)	Triol starter mw	Stripping conditions ³	Initiation ⁴ time (min)
1	A	177	450	vacuum/ nitrogen	5
C2	A	177	450	vacuum only	46
3	A	113	700	vacuum/ nitrogen	2
4	A	113	700	vacuum/ air	5
C5	A	113	700	vacuum only	22
6	B	1143	700	vacuum/ nitrogen	12
C7	B	1143	700	vacuum only	16
8	C	114	700	vacuum/ nitrogen	14
C9	C	114	700	none	> 80
10	D	113	700	vacuum/ nitrogen	30
C11	D	113	700	vacuum/ nitrogen ⁵	105
C12	D	113	700	vacuum only	65
¹ Zinc hexacyanocobaltate catalysts: A = t-butyl alcohol complex, paste, (30% solids), prepared as in Serial No. 08/588,751. B = glyme complex, powder, prepared as in U.S. Pat. No. 5,158,922. C = t-butyl alcohol/ 1K poly(PO) diol complex, prepared as in U.S. Pat. No. 5,482,908. D = t-butyl alcohol complex, powder, prepared as in U.S. Pat. No. 5,470,813. ² Concentration in polyol starter on a solids weight basis. ³ Both catalyst and starter are stripped under vacuum at 130°C. ⁴ Time needed for a 50% drop in initial pressure. ⁵ Starter only is stripped.					

Table 2. Effect of Improved Stripping on Initial Catalyst Activity					
Ex #	Catalyst ¹	Amt. ² (ppm)	Starter	Stripping conditions ³	Initial K _{app} ⁴ (min ⁻¹)
13	C	114	400 mw diol	vacuum/ nitrogen	0.30
C14	C	114	400 mw diol	none	0.058
15	C	114	700 mw triol	vacuum/ nitrogen	0.28
C16	C	114	700 mw triol	none	0.069
¹ Zinc hexacyanocobaltate catalyst "C" is a t-butyl alcohol/ 1K poly(PO) diol complex, prepared as in U.S. Pat. No. 5,482,908. ² Concentration in polyol starter on a solids weight basis. ³ Both catalyst and starter are stripped under vacuum at 130°C. ⁴ Rate constant as measured from a straight-line plot of exponential decay in partial pressure of propylene oxide as a function of time.					

The foam from Polyol B has foam force-to-crush values of 349/122/95 for cycles 1-3.

The results demonstrate that a higher-quality foam is available from polyols made from starter/catalyst mixtures that are stripped according to the process of the invention.

Table 3. Effect of Stripping on Polyol Properties ¹							
Ex #	Product	Stripping conditions ²	PO press. (psia)	Initiation time (min)	Viscosity (cps)	M _w /M _n	Unsat. (meq/g)
17	4K diol	vac/nitrogen	25	11	944	1.15	0.0039
18	4K diol	vac/nitrogen	15	12	912	1.13	0.0039
C19	4K diol	vac only	25	79	1010	1.30	0.0049
C20	4K diol	none	25	> 100	1124	1.44	0.0051
C21	4K diol	none	25	45	1033	1.35	0.0047
22	6K triol	vac/nitrogen	25	5	1372	1.10	0.0041
23	6K triol	vac/nitrogen	12	6	1357	1.05	0.0040
C24	6K triol	none	25	49	1554	1.19	0.0045
C25	6K triol	none	40	25	1540	1.15	0.0042
26	3K triol	vac/nitrogen	25	2	615	1.07	0.0037
C27	3K triol	none	25	46	656	1.17	0.0038
¹ Zinc hexacyanocobaltate catalyst used is "D," a t-butyl alcohol complex, prepared as in U.S. Pat. No. 5,470,813, used at 25 ppm in the final polyol. ² Both catalyst and starter are stripped under vacuum at 130°C.							

The preceding examples are meant only as illustrations; the following claims define the scope of the invention.

We claim:

1. A process which comprises:
 - (a) mixing a polyol starter with a double metal cyanide catalyst; and
 - (b) heating the starter/catalyst mixture under vacuum under conditions effective to achieve improved stripping compared with that which can be achieved through conventional vacuum stripping.
2. The process of claim 1 wherein the starter/catalyst mixture is heated under vacuum while sparging the mixture with an inert gas.
3. The process of claim 2 wherein the inert gas is selected from the group consisting of nitrogen, air, carbon dioxide, argon, helium, and mixtures thereof.
4. The process of claim 2 wherein the starter/catalyst mixture activates at least about 3 times faster in an epoxide polymerization process compared with a starter/catalyst mixture that is not sparged with an inert gas.
5. The process of claim 1 wherein the starter/catalyst mixture is heated under vacuum while stripping the mixture in the presence of an organic solvent.
6. The process of claim 5 wherein the organic solvent is selected from the group consisting of ethers, esters, ketones, alcohols, hydrocarbons, halogenated hydrocarbons, and mixtures thereof.
7. The process of claim 1 wherein the polyol starter is selected from the group consisting of tripropylene glycol, polyoxyalkylene glycols, polytetramethylene ether glycols, propoxylated glycerol, alkoxylated allylic alcohols, and mixtures thereof.
8. The process of claim 1 wherein the catalyst is a zinc hexacyanocobaltate.

9. The process of claim 1 wherein the catalyst is substantially non-crystalline.

10. The process of claim 1 wherein the starter/catalyst mixture is heated at a temperature within the range of about 60°C to about 200°C and under a vacuum of less than about 300 mm Hg.

11. The process of claim 1 further comprising polymerizing an epoxide in the presence of the stripped starter/catalyst mixture to produce a polyether polyol.

12. The process of claim 11 further comprising using the polyether polyol to make a flexible polyurethane foam.

13. A process which comprises:

- (a) mixing a polyol starter with a zinc hexacyanocobaltate catalyst; and
- (b) heating the starter/catalyst mixture at a temperature within the range of about 60°C to about 200°C and under a vacuum of less than about 300 mm Hg while sparging the mixture with an inert gas.

14. The process of claim 13 wherein the inert gas is selected from the group consisting of nitrogen, air, carbon dioxide, argon, helium, and mixtures thereof.

15. The process of claim 13 wherein the polyol starter is selected from the group consisting of tripropylene glycol, polyoxyalkylene glycols, polytetramethylene ether glycols, propoxylated glycerol, alkoxylated allylic alcohols, and mixtures thereof.

16. The process of claim 13 wherein the starter/catalyst mixture activates at least about 3 times faster in an epoxide polymerization process compared with a starter/catalyst mixture that is not sparged with an inert gas.

17. A process which comprises:

- (a) mixing a polyol starter with a zinc hexacyanocobaltate catalyst; and
- (b) heating the starter/catalyst mixture at a temperature within the range of about 60°C to about 200°C and under a vacuum of less than about 300 mm Hg while stripping the mixture in the presence of an organic solvent.

18. The process of claim 17 wherein the organic solvent is selected from the group consisting of ethers, esters, ketones, alcohols, hydrocarbons, halogenated hydrocarbons, and mixtures thereof.

19. The process of claim 17 wherein wherein the polyol starter is selected from the group consisting of tripropylene glycol, polyoxyalkylene glycols, polytetramethylene ether glycols, propoxylated glycerol, alkoxyated allylic alcohols, and mixtures thereof.

20. A process which comprises heating a polyol starter under vacuum under conditions effective to achieve improved stripping compared with that which can be achieved through conventional vacuum stripping.

21. The process of claim 20 wherein the stripped polyol starter has a water content of less than about 100 ppm.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 98/02098

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 B01J37/00 C08G65/10		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 6 B01J C08G		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 470 813 A (LE-KHAC BI) 28 November 1995 cited in the application see column 9, line 12 - column 9, line 17	1,7-12, 20,21
Y	see examples 6,7 -----	2,3, 13-15
X	US 5 482 908 A (LE-KHAC BI) 9 January 1996 cited in the application see column 7, line 24 - column 7, line 29 -----	1,7-12, 20,21
Y	US 5 416 241 A (RUSZKAY JUDE T) 16 May 1995 see column 5, line 35 - column 5, line 43 -----	2,3, 13-15
<div style="display: flex; justify-content: space-between;"> <input type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex. </div>		
* Special categories of cited documents :		
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&" document member of the same patent family</p> </div> </div>		
Date of the actual completion of the international search <div style="text-align: center; font-weight: bold;">1 September 1998</div>		Date of mailing of the international search report <div style="text-align: center; font-weight: bold;">14/09/1998</div>
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer <div style="text-align: center; font-weight: bold;">Schwaller, J-M</div>

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/EP 98/02098

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5470813 A	28-11-1995	AU 5228196 A	01-08-1996
		AU 7901894 A	01-06-1995
		BR 9404711 A	08-08-1995
		CA 2134596 A	24-05-1995
		CN 1107482 A	30-08-1995
		EP 0654302 A	24-05-1995
		HU 71626 A	29-01-1996
		JP 7196778 A	01-08-1995
		US 5589431 A	31-12-1996
		US 5731407 A	24-03-1998
		ZA 9409079 A	02-05-1996
US 5482908 A	09-01-1996	AU 688548 B	12-03-1998
		AU 3048795 A	21-03-1996
		BR 9503975 A	24-09-1996
		CA 2157312 A	09-03-1996
		CN 1133300 A	16-10-1996
		EP 0700949 A	13-03-1996
		HU 73052 A	28-06-1996
		JP 8104741 A	23-04-1996
		SG 32489 A	13-08-1996
		US 5536883 A	16-07-1996
		ZA 9507474 A	09-04-1996
US 5416241 A	16-05-1995	CA 2140499 A	28-07-1995
		EP 0665254 A	02-08-1995
		JP 7238161 A	12-09-1995